

**SUPERWELD 309L**



SUPERWELD 309L is a rutile basic coated low carbon grade electrode of the 23% chromium and 12% nickel type. It is recommended for welding corrosion resistant and heat resistant steels of the AISI 309 type, which is often used for furnace parts, aircraft components, heat exchangers and chemical processing equipment.

SUPERWELD 309L can also be used for welding dissimilar carbon manganese steels and low alloy steels, welding stainless steels to mild steels and as a buffer for hardfacing applications.

**CLASSIFICATIONS**

AWS	A5.4	E309L-16
BS EN	1600	E 23 12 LR12

**CHEMICAL ANALYSIS**

% Carbon	0.034	% Nickel	13.50
% Manganese	1.50	% Sulphur	0.01
% Silicon	0.45	% Phosphorous	0.01
% Chromium	23.60		

**TYPICAL MECHANICAL PROPERTIES  
(ALL WELD METAL IN THE AS WELDED  
CONDITION)**

0,2% Proof Stress	420 MPa min
Tensile Strength	550 - 650 MPa
% Elongation on 4D	30 min
Charpy V-Notch at +20°C	55J min
Charpy V-Notch at -70°C	40J min
Hardness VPN	170 - 200

**PACKING DATA**

(DC + AC 70 OCV min)

Diameter (mm)	Electrode Length (mm)	Current Amps	Item Number Multi-Kg pack	Pack Mass (Kg)
2.5	300	50 - 85	085-772	3 x 5
3.25	350	80 - 120	085-773	3 x 5
4	350	100 - 150	085-774	3 x 5

The information contained or otherwise referenced herein is presented only as typical without guarantee or warranty, and Afrox expressly disclaims any liability incurred from any reliance thereon. No data is to be construed as recommended for any welding condition or technique not controlled by Afrox.

For more information contact the Afrox Customer Service Centre,  
tel: 0860 020202 or e-mail: [customer.service@afrox.boc.com](mailto:customer.service@afrox.boc.com)  
Website: [www.afrox.com](http://www.afrox.com)

